



Boral Cement - Dry Graded Sands

Boral Cement Limited
ABN 62 008 528 523

Maldon Bridge Road Picton NSW 2571

T +61 2 4640 0200

F +61 2 4677 1487

www.boral.com.au

Average as of Feb 2013

Typical Grading - % Passing

	20mm	12mm	6mm	5mm	3mm	2mm	1mm	900	FW	30/60	F6	TN	AB
26.0mm	97												
19.0mm	36												
13.2mm	2	100											
9.50mm	1	70											
6.70mm		12	100										
5.60mm		6	91	-									
4.75mm		3	61	99	-								
3.35mm			15	84	100	-							
2.80mm			4	57	79	100							
2.36mm			3	35	48	98							
2.00mm				10	16	82	-						
1.70mm				4	3	50	100						
1.40mm				-	1	14	92						
1.18mm					-	4	70	-		-			
1.00mm						1	44	100	100	100			
0.850mm							18	98	100	-			
0.710mm								77	-	99	-	-	
0.600mm							1	55	84	-	100	100	
0.500mm								-	-	33	-	-	-
0.425mm								7	-	-	94	97	100
0.300mm								-	26	1	35	58	95
0.212mm									-	-	-	16	29
0.150mm									2	0	0	2	1

Note: Typical grading analysis based on average results.

Actual results including Min/Max are available on request.